



Manufacturer
of
Specialty
Chemicals

GMT Corporation

Address : 901-5 Jangcheon-Ro, Cheoncheon-Myeon
Jangsoo-Kun, Jeonbook, 597-851 Korea

Phone : +82-63-353-2470 Fax : +82-63-353-2471

e-mail : gmt@gmt-chem.co.kr

<http://www.gmt-chem.co.kr>

GMT-1816 / GMT-1816F for Emulsion

● Standard Formulation(35% Solid Content)

- GMT-1816, GMT-1816F	:	100
- LA 9mole	:	35
- KOH(90%)	:	2.0
- SmBS	:	0.7
- Water	:	255

● Emulsion Procedure

1. Put all the ingredients into a vessel at a time
2. Increase the temperature until 145°C
Pressure is over 4 kgf
3. Remove the air of the top space of the vessel by replacing with steam or nitrogen
4. Maintain the temperature for 1-2 hours
5. Shock cooling : 140°C -----> 80°C within 15 minutes, or

Transfer the reactant to the other cold vessel in a few minutes